

DIMENSIONS

FORMAT

Length	1261 mm
Width	192 mm
Number of panels per pack	10
m ² per pack	2.421
Bevels	-
Thickness	7.0 mm
Tongue and groove	Uniclic

FACTORY WARRANTY

	METHOD	PARAMETERS	VALUES
Usage class	EN 13329		Class
CE	EN 14041		21-22-23/31-32
Warranty	Residential use	See warranty conditions	
	Commercial use	See warranty conditions	

GENERAL DATA (ACCORDING TO EN 13329)

	METHOD	PARAMETERS	NORM REQUIREMENTS	VALUES
Wear resistance	EN 13329		≥ 4000 cycles	≥ 4000 cycles
Wear class	EN 13329		AC4	AC4
Impact resistance	EN 13329	Small ball	≥ 12 N	≥ 12 N
		Big ball	≥ 750mm	≥ 750mm
Scratch resistance Effect of a castor chair	EN 438-2, 25		Charge ≥ 3N	Charge ≥ 3N
Thickness swelling	ISO 24336	Type W (EN 12529)	25000 cycles	No change
		After 24h immersion at 20°C	≤ 18%	≤ 18%
Locking strength	ISO 24334	FlO,2 long side	≥ 1 kN/m	≥ 1 kN/m
		FsO,2 short side	≥ 2 kN/m	≥ 2 kN/m
		Fmax long side	≥ 1 kN/m	≥ 1 kN/m
		Fmax short side	≥ 2 kN/m	≥ 2 kN/m
Effect of a furniture leg	EN 424		No damage shall be visible, when tested with foot type O	No visible damage
Resistance to staining	EN 438	Group 1,2	Class 5	Class 5
		Group 3	Class 4	Class 4
Light fastness	EN ISO 4892 2:2006/A1:2009 Procedure B - Cycle 5	Grey reference	Class ≥ 4	Class 4

ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	VALUES
Formaldehyde emission	EN 717-1	ppm	E1 < 0,1	< 0,01
Anti-static	EN 1815		≤ 2,0 kV	≤ 2,0 kV
Reaction to fire Thermal resistance Slip resistance	EN 13501-1	Class		Cfl-s1
	EN 12667	m ² K/W		0,051 m ² K/W
	EN 13893	μ	μ ≥ 0,30	DS: μ ≥ 0,30

Clear form



EN14041:2004/AC:2006
Laminate floor coverings EN13329:2006+A1

Save