

Eclipse 50

Heterogeneous Vinyl

Technical Data Sheet

Warranty period (years)			10
Usability class	PN-EN ISO 10874		33/42
Total thickness	PN-EN ISO 24346		2,20 mm
Thickness of wear layer	PN-EN ISO 24340		0,50 mm
Weight	PN-EN ISO 23997		1,95 kg/m ²
Reaction to fire	PN-EN 13501-1		Bfl-s1
Slip resistance	PN-EN 13893		≥ 0,3 DS
Slip resistance	DIN 51130		R10
Electrical properties	PN-EN 14041		Antistatic and dissipating
Electrical resistance	PN-EN 1081		< 1,0 x 10 ⁹ Ω
Impact sound reduction	PN - EN ISO 717-2		13 dB
Residual indentation	PN-EN ISO 24343-1		≤ 0,20 mm
Effect of castor chair	PN-EN ISO 4918		No visible damage
Chemical resistance	PN-EN ISO 26987		Resistant
Electrostatic voltage	PN-EN 1815		< 2,0 kV
Binder content	PN-EN ISO 11638	-	Typ I
Light resistance	PN EN ISO 105-B0		min. 6
Dimensional stability	PN-EN ISO 23999		max 0,4 %
Roll area	PN-EN ISO 24341		100 m ² / 75 m ² / 50 m ²
Roll width	PN-EN ISO 24341		4 m / 3 m / 2 m
Thermal resistance R ₂₃	PN-EN 12667		0,023 m ² K/W
Underfloor heating	-	-	up to 27°C
Volatile organic compounds (VOC)	PN-EN 16516		0,60 mg/m ³
Formaldehyde emission	PN-EN 16516		E1
Poliuretan PUR SHIELD	-		x
Embossing INVERTECH	-		✓